

**High performance, hand applied, fibre reinforced medium build, high strength, concrete reinstatement mortar conforming to the requirements of BS EN 1504-3 Class R4**

## Uses

For the compatible reinstatement of defects in high strength reinforced concrete structures.

Renderoc HBS is particularly suited to the repair of vertical surfaces and, because of its relatively low fresh wet density, can also be used for overhead repairs.

Renderoc HBS is suitable for repair methods 3.1, 4.4, 7.1, 7.2 as defined by BS EN 1504-3.

## Advantages

- Compatible with concrete of compressive strength 35 - 60 N/mm<sup>2</sup>
- High-build applications possible while maintaining higher compressive strengths — fewer cold joints
- Frequently obviates the need for formwork
- Polymer-modification provides extremely low permeability to water and carbon dioxide
- Shrinkage compensated to provide long-term dimensional stability
- One component, pre-bagged to overcome site-batched variations
- Contains no chloride admixtures
- Shade can be varied with Renderoc Lightener / Darkener\*

## Description

Renderoc HBS is supplied as a ready to use blend of dry powders which requires only the site addition of clean water to produce a highly consistent, medium-weight repair mortar.

It is based on Portland cements, graded aggregates, lightweight fillers and chemical additives which provide a mortar with good handling characteristics while minimising water demand. The low water requirement ensures good strength gain and long-term durability.

It can be applied in sections up to 60 mm thickness in vertical locations and up to 50 mm thickness in overhead locations in a single application without the use of formwork.


Thicker sections can be achieved by the use of formwork or can be built up in layers. Deep pockets can sometimes be filled in a single application dependent on the configuration of the pocket and the volume of exposed reinforcing steel.

The material should not be applied at less than 10 mm thickness.

## Standards compliance

Renderoc HBS complies with the classification R4 according to EN 1504-3, repair methods 3.1, 4.4, 7.1 and 7.2.

Renderoc HBS complies with LU Standard 1-085 'Fire Safety Performance of Materials'.

 <b>0370</b> <b>09</b> <b>0370-CPR-0845</b>	
<b>DOP: UK9-51</b>	
<b>Fosroc International Limited</b> Drayton Manor Business Park, Coleshill Road, Tamworth, B78 3XN, UK	
<b>Fosroc® Renderoc HBS</b>	
BS EN 1504:3 Structural and non-structural repair methods 3, 4 and 7	
Compressive strength	Class R4: ≥ 45 MPa
Chloride ion content	≤ 0.05%
Adhesion strength by pull-off test	≥ 2.0 MPa
Thermal compatibility: freeze thaw cycling with immersion	≥ 2.0 MPa
Carbonation resistance	Pass
Elastic modulus	≥ 20 GPa
Reaction to fire	A2 s1 d0
Dangerous substances	Complies with 5.4

\*Refer to separate datasheet

# Fosroc® Renderoc HBS

## Properties

The following results were obtained at a water : powder ratio of 0.13 and a temperature of 20°C unless otherwise stated.

Test method	Standard	EN 1504 R4 Requirement	Result
Compressive Strength	EN 12190:1999	$\geq 45$ MPa	@ 1 Day 20 MPa @ 28 days 45 MPa
Bond strength by pull off:	EN 1542:1999	$\geq 2.0$ MPa	2.1 MPa
Chloride ion content:	EN 1015-17:2000	$\leq 0.05$ %	0.03%
Freeze thaw cycling:	EN 13687-1:2002	$\geq 2.0$ MPa	2.0 MPa
Resistance to carbonation $d_k$	EN 13295:2005	$\leq$ ref concrete	Complies
Elastic Modulus in Compression	EN 13412	$\geq 20$ GPa	25 GPa @ 28 Days
Fire rating	EN 13501-1		Class A2 s1 d0 Non-Combustible
Setting time	BS 4551 Pt 14:1980	-	Initial set: 3 hours Final set: 5 hours
Fresh wet density		-	Nominally 2000 kg/m <sup>3</sup>
Chemical resistance		-	The low permeability of Renderoc HBS severely retards chemical attack in aggressive environments. The cured mortar is impermeable to acid gases and oxygen.
Build Characteristics (hand applied) Minimum thickness: Overhead: Vertical:	-	-	10 mm Up to 50 mm Up to 60 mm

**Clarification of property values:** The typical properties given above are derived from laboratory testing. Results derived from testing field applied samples may vary.

## Application instructions

### Preparation

Form a square edge perimeter to the repair area using appropriate methods (feather edging must be avoided), break out the complete repair area up to a minimum depth of 10mm up to the square edge.

Clean the surface and remove any dust, unsound or contaminated material, plaster, oil, paint, grease, corrosion deposits or algae. Where breaking out is not required, roughen the surface and remove any laitance by light scabbling or abrasive-blasting.

Oil and grease deposits should be removed by steam cleaning, detergent scrubbing or the use of a proprietary degreaser. The effectiveness of decontamination should then be assessed by a pull-off test.

Expose fully any corroded steel in the repair area and

remove all loose scale and corrosion deposits. Steel should be cleaned to a bright condition paying particular attention to the back of exposed steel bars. Abrasive blasting, hydrodem equipment, powered mechanical scraping or other suitable means is recommended for this process.

Where corrosion has occurred due to the presence of chlorides, the steel should be high-pressure washed with clean water immediately after abrasive-blasting to remove corrosion products from pits and imperfections within its surface.

Refer to HSE information sheet CIS36 regarding control of exposure to construction dust, available at [www.hse.gov.uk](http://www.hse.gov.uk).

### Reinforcing steel priming

Apply one full coat of Nitoprime Zincrich Plus and allow to dry before continuing. If any doubt exists about having achieved an unbroken coating, a second application should be made and, again, allowed to dry before continuing.

# Fosroc® Renderoc HBS

---

## Concrete Priming

The concrete substrate should be saturated surface dry immediately before the application of the primer i.e. it should be thoroughly saturated with clean water and any residual surface water removed prior to applying Renderoc Primer.

Under severe drying conditions repeated soaking may be necessary to ensure the substrate is still saturated at the time of application of the primer.

Add 3 parts by volume of Renderoc Primer Part A to 1 part by volume Renderoc Primer Part B (4 to 1 by weight) in a clean mixing vessel and mix with a spatula or slow speed drill until a homogeneous smooth paste is produced.

Scrub Renderoc Primer slurry into the surface.

Renderoc HBS can be applied immediately to the primed surface. If the primer dries apply another coat of primer before continuing.

Open bags of Renderoc Primer Part A should be sealed and stored in a dry area. Use within 14 days.

In exceptional circumstances, e.g. where a substrate/repair barrier is required or where the substrate is water immersed or likely to remain permanently damp, Nitobond EP bonding aid should be used. Contact the local Fosroc office for further information.

## Mixing

Care should be taken to ensure that Renderoc HBS is thoroughly mixed. A forced-action mixer is essential. Mixing in a suitably sized drum using an approved Renderoc Mixing Paddle (MR4) in a slow speed (400/500 rpm) heavy-duty drill is acceptable for the occasional one-bag mix.

Free-fall mixers must not be used. Mixing of part bags should never be attempted.

For normal applications, place 3.25 to 3.5 litres of drinking quality water into the mixer.

With the machine in operation, add one full bag of Renderoc HBS and mix, for a minimum of 3 minutes and a maximum of 5 minutes, until fully homogeneous.

The consistency may be adjusted by the addition of small amounts of water up to the maximum total water content of 3.5litres.

Note that the powder must always be added to the water.

## Mixing warning

As with other 'one pack' repair mortars, Renderoc HBS may exhibit satisfactory handling characteristics even though inadequately mixed. This will result in a significantly lower level of performance or possible failure. It is therefore essential that mixing instructions are strictly adhered to with particular emphasis on the quantity of water used and the time of the mixing operation.

## Application

Exposed steel reinforcing bars should be firmly secured to prevent movement during application.

Apply the mixed Renderoc HBS by gloved hand or trowel, thoroughly compacting onto the primed substrate and around exposed reinforcement.

If sagging or slumping occurs the Renderoc HBS should be completely removed and reapplied at a reduced thickness to a correctly primed substrate.

## Build-up

Additional build-up can be achieved by application of multiple layers.

The surface of the intermediate layers should be comb scratch-keyed and cured with Nitobond AR. Repriming with Renderoc Primer and a further application of Renderoc HBS may proceed as soon as this layer has set.

## Finishing

Renderoc HBS is finished by striking off with a straight edge and closing with a steel float. Wooden or plastic floats, or damp sponges, may be used to achieve the desired surface texture. The completed surface should not be overworked.

## Low temperature working

In cold conditions down to 5°C, the use of warm mixing water (up to 30°C) is advisable to accelerate strength development. Normal precautions for winter working with cementitious materials should then be adopted. The material should not be applied when the substrate and/or air temperature is 5°C and falling. At 5°C static temperature or at 5°C and rising, the application may proceed.

## High temperature working

At ambient temperatures above 35°C, the material should be stored in the shade and cool water used for mixing.

## Curing

Renderoc HBS is a cement-based repair mortar. In common with all cementitious materials, it must be cured immediately after finishing in accordance with good concrete practice. The use of Nitobond AR, sprayed on to the surface of the finished mortar in a continuous film, is recommended. A low pressure atomising sprayer is essential for applying the Nitobond AR. Any excessive run-off on verticals or drips on soffits should be removed by brush before they harden.

Large areas should be cured as trowelling progresses (0.5m<sup>2</sup> at a time) without waiting for completion of the entire area.

In fast drying conditions, supplementary curing with polythene sheeting taped down at the edges must be used. In cold conditions, the finished repair must be protected from freezing.



# Fosroc® Renderoc HBS

## Overcoating with protective decorative finishes

Renderoc HBS is extremely durable and will provide long-term protection to the embedded steel reinforcement within the repaired locations. The surrounding parts of the structure will benefit from the application of a barrier/decorative coating to limit the advance of chlorides and carbon dioxide, bringing them to the same protective standard as the repair itself. Fosroc recommend the use of the Dekguard range of protective, anti-carbonation coatings. These products provide a decorative and uniform appearance as well as protecting areas of the structure which might otherwise be at risk from the environment. Dekguard products may be applied over the repair area without prior removal of the Nitobond AR curing membrane. Other curing membranes must be removed prior to the application of Dekguard products.

## Cleaning

Renderoc HBS and Renderoc Primer should be removed from tools, equipment and mixers with clean water immediately after use. Cured material can only be removed mechanically. Clean tools used with Nitoprime Zincrich Plus and Nitobond EP before material cures, using Fosroc Solvent 102.

## Estimating

### Supply

Renderoc HBS:	25 kg bags
Nitoprime Zincrich Plus:	1.9 litre and 800 ml cans
Renderoc Primer:	20 Kg Part A + 5 litres part B
Handy Pack:	4 Kg Part A + 1 litre Part B
Nitobond AR:	5 and 25 litre drums
Fosroc Solvent 102:	5 and 25 litre tins

### Coverage and yield

Renderoc HBS:	Approximately 14 litres / 25kg bag (approximately 1.4 m <sup>2</sup> at 10 mm thickness)
Nitoprime Zincrich Plus:	8 m <sup>2</sup> /litre
Nitobond AR:	6 - 8 m <sup>2</sup> / litre
Renderoc Primer	Approx. 13 litres - 2m <sup>2</sup> /litre Handy pack 2.5 litres - 2m <sup>2</sup> / litre

Notes: the actual yield per bag of Renderoc HBS will depend on the consistency used.

## Limitations

Renderoc HBS should not be used when the temperature is below 5°C and falling. Do not mix part bags. Due to the lightweight nature of Renderoc HBS, the product should not be used in areas subjected to traffic (in these circumstances, Renderoc S should be considered).

Renderoc HBS should not be exposed to moving water during application. Exposure to heavy rainfall prior to the final set may result in surface scour.

Where compatibility with lower strength concrete is required, Renderoc GP should be used.

If any doubts arise concerning temperature or substrate conditions, consult the local Fosroc office.

## Storage

The product has a shelf life of 12 months from the date of manufacture if kept in dry storage in the original, unopened bags. If stored at high temperatures and/or high humidity the shelf life may be reduced to less than 6 months.

Nitobond AR and Renderoc Primer Part B should be protected from frost.

## Precautions

### Health and safety

For further information refer to the appropriate Safety Data Sheets available at [www.fosroc.com](http://www.fosroc.com).

### Fire

Renderoc HBS is non-flammable.

Nitoprime Zincrich Plus and Fosroc Solvent 102: are flammable. Keep away from sources of ignition. No Smoking. In the event of fire, extinguish with CO<sub>2</sub> or foam. Do not use a water jet

### Flash points

Nitoprime Zincrich Plus:	41°C
Fosroc Solvent 102:	33°C

## Environmental Data (EPD)

GWP Total, A1 – A3: 0.419 kgCO<sub>2</sub>e per 1kg product.

GWP Total, A1 – D: 0.663 kgCO<sub>2</sub>e per 1kg product.

Fosroc and Renderoc are trademarks of Fosroc International Limited



## Fosroc International Limited

Drayton Manor Business Park  
Coleshill Road, Tamworth,  
Staffordshire B78 3XN. UK

[www.fosroc.com](http://www.fosroc.com)

### Important note

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard Conditions for the Supply of Goods and Services, copies of which may be obtained on request. Whilst Fosroc endeavours to ensure that any advice, recommendation, specification or information it may give is accurate and correct, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products, whether or not in accordance with any advice, specification, recommendation or information given. All Fosroc datasheets are updated on a regular basis. It is the user's responsibility to obtain the latest version.

telephone:  
+44 (0) 1827 262222

email:  
[enquiryuk@fosroc.com](mailto:enquiryuk@fosroc.com)

