

DENSOCLAD 50 TAPE

DESCRIPTION

A medium duty tape, designed to protect small and medium diameter pipes, welded joints, bends and fittings. The tough yet conformable pvc backing provides excellent resistance to damage during handling and backfilling. For the anti-corrosion protection of buried or immersed pipes and fittings. Suitable for machine or hand application.

COMPOSITION

A thick polymer bitumen adhesive laminated to a tough plasticised pvc backing. The adhesive layer is protected by an interleaving, wider than the tape, which is removed during application.

TYPICAL PROPERTIES	TEST METHOD	DATA
Colour		Black
Breaking Strength	ASTM D1000	9 N/mm
Elongation at Break	ASTM D1000	260%
Tear Strength	ASTM D1004	25 N
Adhesion <i>To Primed Steel</i> <i>To Self</i>	ASTM D1000 24 hrs ASTM D1000 24 hrs	3.0 N/mm 3.0 N/mm
Impact Strength	ASTM G14	4 Nm
Dielectric Strength	ASTM D1000	30 kV
Insulation Resistance	BS 2782	10 ⁶ MegOhm
Resistance to Cathodic Disbonding	ASTM G8 30 day	Excellent
Resistance to Acids, Alkalis and Salts		Excellent
Temperature Range <i>For Application</i> <i>For Service</i>		+5°C to +45°C -20°C to +60°C
Roll Length		12m (other lengths to order)
Width		50-300mm
Core Size		76mm I.D.
Thickness <i>PVC Backing</i> <i>Adhesive</i> <i>Total</i>	ASTM D1000	0.37mm 0.75mm 1.12mm
Weight		1.3 kg/m ²

cont'd.../2



DENSOCLAD 50 TAPE (cont'd)

RECOMMENDED PRIMER	Denso Primer D
APPLICATION	See Instruction leaflet 296/6/90 supplied with each carton.

Important

Winn & Coales (Denso) Ltd pursue a policy to develop and continually improve all of our products and therefore the information given in this data sheet is intended as a general guide and does not constitute a warranty of specification. However, our sales personnel are committed to assist the user in establishing the suitability of the product for its intended purpose and additional specific information is available on request.

Winn & Coales (Denso) Ltd operate a Quality Management System registered to BS EN ISO 9001 (Certificate No. FM01548).

Winn & Coales (Denso) Ltd, Denso House, Chapel Road, London SE27 0TR, United Kingdom
Tel: +44 (0) 20 8670 7511 Fax: +44 (0)20 8761 2456 Email: mail@denso.net Website: www.denso.net
