

ARBOKOL AG2 POROUS PRIMER

ARBOKOL AG2 Porous Primer is a one-part, solvent containing, air drying isocyanate resin-based primer.

Main Applications

Recommended for use in conjunction with ARBOKOL AG2 and ARBOKOL 2150 two-part polysulphide sealants for the priming of porous surfaces such as concrete.

Application Instructions

The joint surfaces must be clean, dry and free from all contamination. The surfaces should be degreased using the appropriate ARBO® Cleaner. Apply one coat of ARBOKOL AG2 Porous primer using a clean dry brush and allow it to dry for at least 1 hour but not more than 8 hours before applying the sealant. Strictly adhere to the user instructions on the tin.

All joint preparation and priming should be carried out in accordance with BS 8000-16:1997+A1 2010, the British Standard for the sealing of joints in buildings using sealants.

Consult ARBO Technical Services regarding the use of primer in specific instances.





ARBOKOL AG2 Porous Primer

Storage Life

9 months in original unopened package stored in a cool, dry place out of direct sunlight.

Health and Safety

For full information please consult the Safety Data Sheet.

Packaging

ARBOKOL AG2 Primer is supplied in 500ml and 5 Litre containers.

N.B. Yield approximately 125 metres per 500ml, 1250 metres per 5 litre.

Technical Data	
Colour:	Colourless, yellowish
Density	Approx 1.0 g/cm ³
Application Temperature:	+ 5° C to + 30° C
Cleaning:	Tools must be carefully cleaned immediately after use with an appropriate cleaner.

Important: The information in this leaflet is given in good faith and based on results gained from experience and tests. However, all recommendations or suggestions are made without guarantee since the conditions of use are beyond our control. It is the user and specifier's responsibility to ensure ARBO product is suitable for the intended use: consult ARBO Technical Services for specific advice. Goods are supplied subject to the Company's terms and conditions of sales, a copy of which is available on request.



