



Constructive solutions

Fosroc Nitoseal Primer MS2

Two component solvent based epoxy resin primer.

Description

Nitoseal Primer MS2 primer is designed for priming before application of the sealant.

Advantages

- Easy to Apply
- Strong adhesion

Application

Empty the entire contents of the hardener tin into the base tin, replace base tin lid. Mix thoroughly, by shaking for 2 minutes.

Prime the joint face using a clean dry brush. Avoid over application of primer causing puddles in the bottom of the joint. Sealants should be applied between 30 minutes and 4 hours after priming.

If the joint is not sealed overnight the primer film should be removed by grit blasting or grinding and the joint reprimed. The mixed Primer MS2 must be applied within one working day. Do not use part packs.

Cleaning

Clean equipment immediately after use with Fosroc Solvent 102.

Estimating

Supply

Primer MS2:	500 ml can
Fosroc Solvent 102:	4 litre can

Storage

Shelf life

12 months if stored in the original unopened packs in a cool dry place. Do not store in direct sunlight.

Precautions

Health and safety

Nitoseal Primer MS2 may be harmful if swallowed or inhaled and may cause skin and eye irritation. Product contains a very small amount of isocyanates and low flash point solvent.

Should accidental skin contact occur, remove contaminated clothing and wash with warm soapy water. Do not scrub.

If inhaled remove person to fresh air. Get medical advice if breathing becomes difficult. In case of contact with eyes, rinse immediately with plenty of clean water for at least 15 minutes and seek medical advice. If swallowed, give a glass of water to dilute and seek medical attention immediately - do not induce vomiting. For further information, refer to the appropriate Product Material Safety Data Sheet.

Fire

Nitoseal Primer MS2 and Solvent 102 is highly flammable liquid. Keep away from sources of ignition. No smoking. Containers should be tightly sealed when not in use. In the event of fire, extinguish with CO₂ or foam. Do not use water jet.

Disposal

Dispose according to local authority regulations. Do not dispose down drains or into local waterways.

For further information on any of the above, please consult your local Fosroc office - as below.

Additional information

	Primer MS2
Flash point:	23°C
Storage life:	12 months
Drying time:	20 to 60 mins.
Flash point - Fosroc Solvent 102:	33°C

For further info please contact your local Fosroc office.

Important note

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard Conditions for the Supply of Goods and Service. All Fosroc datasheets are updated on a regular basis. It is the user's responsibility to obtain the recent version.

Head Office

telephone: (+9714) 2039699

fax: (+9714) 2859649

email: agf@fosroc.com

Regional offices

Abu Dhabi, Al Gurg Fosroc
Bahrain, YBA Kano
Kuwait, Boodai
Oman, Al Amana

telephone: 673 1779
telephone: 17738200
telephone: 4817618
telephone: 24815080

fax: 673 1449
fax: 17738288
fax: 4832124
fax: 2481755

email: abudhabi@fosroc.com
email: bahrain@fosroc.com
email: kuwait@fosroc.com
email: oman@fosroc.com

ISO 9001
ISO 14001
ISO 45001
BUREAU VERITAS
Certification



Al Gurg Fosroc Co. LLC

Post Box 657, Dubai
United Arab Emirates
www.fosroc.com

UAE/0672/10/A